



Item Code	
Description	Exposed round thermostatic shower full sytem
Recommended Water Pressure	1-5 Bar
Standard	EN1111:2017
Test Report Available	EN1111:2017
Chemical composition Specific	<p>Brass Ingot: Cu (57.0-60.0), Al (<=0.2), Fe (<=0.5), Ni (<=1.0), Pb (0.8-1.9), Sb (=0.01), Sb (<=0.003), P (<=0.02), Zn (Remainder)</p> <p>Brass Rod: Cu (57.0-60.0), Pb (<=0.5), Total Impurity (<=0.3), Fe (<=0.5), Ni (<=1.0) Zn (Remainder)</p> <p>Stainless steel 304: Cr (17.0-19.0), Ni (8.0-10.0), Mn (<=2.0), p (<=0.35), s (<=0.03), Si (<=1.0), C(<=0.07)</p> <p>Zinc Alloy: Al (3.9-4.3), Mg (0.03-0.06), Fe (<=0.03), Cu (<=0.03), Pb (<=0.003), Cd (<=0.003), Sn (<=0.001), Zn (Remainder)</p>
Finish	Plating: Nickel ~8 um, Chromium ~0.2 um; Salty Spray Test (AASS24H)
Color Availalbe	Chrome, Matt Black, Brushed Gold Titanium
NOTE	The information presented subject to changes due to requirements in different sites, markets and/ or countries. PESEN reserves the right to make the necessary amendments at any time without prior notice.